



INTERNATIONAL JOURNAL OF PURE AND APPLIED RESEARCH IN ENGINEERING AND TECHNOLOGY

A PATH FOR HORIZING YOUR INNOVATIVE WORK

EFFECT OF CRUMB RUBBER ON WORKABILITY OF GEOPOLYMER CONCRETE

VISHAL D ASUDIA¹, PRASHANT B PARMAR¹, KIRAN B VAHONIYA¹, ABHIJITSINH PARMAR²

1. U.G. Student, Department of Civil Engineering, SVBIT, Gandhinagar.
2. Assistant Professor, Department of Civil Engineering, SVBIT, Gandhinagar.

Accepted Date: 27/02/2016; Published Date: 01/03/2016

Abstract: - Geopolymers are new materials for fire and heat-resistant coatings and adhesives, medicinal applications, high-temperature ceramics, new binders for fire-resistant fiber composites, toxic and radioactive waste encapsulation and new cements for concrete.[1] In this study crumb rubber(Waste material) was used for the replacement of conventional fine aggregates to find out the possible best replacement of conventional fine aggregate. From the study it indicates that replacement by crumb rubber is reducing the workability of Geopolymer concrete.

Keywords: Fly Ash, Crumb Rubber, Geopolymer Concrete, alkaline solution



PAPER-QR CODE

Corresponding Author: MR. ABHIJITSINH PARMAR

Access Online On:

www.ijpret.com

How to Cite This Article:

Abhijitsinh Parmar, IJPRET, 2016; Volume 4 (7): 179-185

INTRODUCTION

Geopolymers are novel materials intended for fire and heat-resistant coatings and adhesives, medicinal applications, high-temperature ceramics, novel binders for fire-resistant fiber composites, toxic and radioactive waste encapsulation and novel cements for concrete [2].

The properties and utilize of geopolymers are being explored in numerous scientific and industrial disciplines: recent inorganic chemistry, physical chemistry, colloid chemistry, mineralogy, geology, and in further types of engineering practice technologies.

Geopolymers are division of polymer science, chemistry and technology that forms one of the most important areas of materials science. Polymers are either organic material, i.e. carbon-based, or inorganic polymer, for example silicon-based.

The organic polymers comprise the classes of natural polymers (rubber, cellulose), synthetic organic polymers (textile fibers, plastics, films, elastomers, etc.) and natural biopolymers (biology, medicine, pharmacy) [3]. Raw materials used in the synthesis of silicon-based polymers are mainly rock-forming minerals of geological origin [4].

Materials:

a. Fly ash

Fly ash used in this study was unprocessed fly ash from torrent power plant (locally available). The whole quantity of fly ash was obtained from one batch. Later, Fly ash was used in small proportions in mass concreting for dams and other hydraulic.

b. Course Aggregates & Fine aggregate

Locally available crushed stones of 10 mm and 20 mm aggregates were used as coarse aggregates. Local river sand and crumb rubber was used as fine aggregate in the concrete mixtures.

c. Alkaline Solution as binder materials

The alkaline liquid used was a combination of sodium silicate solution and sodium hydroxide solution. The sodium silicate solution (NaOH = 15.38%, Na₂SiO₃ = 46,15%, and water = 38.46% by mass) was purchased from a local supplier in bulk. The sodium hydroxide (NaOH) in flakes or pellets from with 97%-98% purity was also purchased from a local supplier in bulk. The NaOH solids were dissolved in water to make the solution. To make alkaline solution first of all to

prepare 10 M solution 400 grams of NaOH are dissolved in 1000 gm of water than 1200 grams of Na₂SiO₃ are added in dissolved solution. Then this solution kept as it for 24 hours at normal room temperature.

Mix Proportion:

Table 1-Mix Design

Mix Design	Fly Ash(kg)	Fine Aggregate(kg)	Coarse Aggregate(kg)	Alkaline Solution	Crumb Rubber (kg)	% of Replacement
M0	469.33	554.07	1212.44	462.22	0	0
M1	469.33	498.663	1212.44	462.22	55.407	10%
M2	469.33	443.256	1212.44	462.22	110.814	20%
M3	469.33	387.849	1212.44	462.22	166.221	30%
M4	469.33	332.442	1212.44	462.22	221.628	40%
M5	469.33	277.035	1212.44	462.22	277.035	50%



Fig. - 1 Mixing of Alkaline solution with Fly Ash and Aggregates

Workability Tests

a) Slump Test:

To determine the workability of concrete mix by slump test conducted by as per IS 1199-1959. The internal surface of the mould thoroughly cleaned and freed from superfluous moisture than mould placed on a smooth, horizontal, rigid and nonabsorbent surface. The mould was filled in four layers, each approximately one-quarter of the height of the mould. Each layer was tamped with twenty-five strokes of the rounded end of the tamping rod. The bottom layer tamped throughout its depth. After the top layer has been rodded, the concrete was struck off level with a trowel or the tamping rod, so that the mould is exactly filled. The mould removed from the concrete immediately by raising it slowly and carefully in a vertical direction. This allows the concrete to subside and the slump shall be measured immediately by determining the difference between the height of the mould and that of the highest point of the specimen being tested.



Fig. – 2 Slump Test

b) Compaction Factor Test:

The concrete was placed gently in upper hopper, using the hand scoop. The hopper was filled level with its brim and trap door was opened so concrete falls in to lower hopper. Then the trapdoor of second hopper was opened and concrete was allowed to fall in cylinder. The excess concrete above the top of cylinder was removed by towel. The weight of concrete was measured and compare that with the weight of concrete was fully compacted in same cylinder and the ratio of both known as compaction factor.



Fig. – 3 Compaction Factor Test

Result:

(Table 2-Slump test results)

Mix Proportion	Slump(mm)
M0	110
M1	102
M2	94
M3	85
M4	71
M5	70

(Table 3-C.F. Test results)

Mix Proportion	C.F.
M0	0.95
M1	0.95
M2	0.94
M3	0.94
M4	0.93
M5	0.92

CONCLUSION:

In this study of replacement of fine aggregates with Crumb rubber, we got maximum workability when replacement percentage is zero and minimum workability when replacement percentage is 50. Replacement of Fine aggregates with Crumb Rubber will reduce the workability of Concrete. Increase in the percentage of replacement of aggregate will decrease the workability of Geopolymer concrete.

REFERENCES

1. Ankush Chakravorty, Raj Khatri, Tejkuvarba, Abhijitsinh Parmar, "EFFECT OF AGGREGATE SIZE AND SILICA FUME ON THE WORKABILITY OF GEOPLOYMER CONCRETE", International Journal of Research in Engineering and Technology, Volume: 03 Issue: 04, Apr-2014
2. Michael J. Gibbs, Peter Soyka and David Conneely - CO2 Emissions from cement production, (ICF Incorporated). It was reviewed by Dina Kruger (USEPA).
3. Stevenson, M., and Panian, L. - "Sustainability through Strength," Concrete International, V. 31, No. 3, Mar. 2009, pp. 34-39.
4. Raijiwala D.B. Patil H. S. - Geopolymer concrete: A concrete of next dicade.
5. Joseph Davidovits - Geopolymer chemistry & application 2nd edition (June 2008), Institute Geopolymer, France

6. Prof. M. A. Bhosale, Prof. N. N. Shinde - Geopolymer Concrete by Using Fly Ash in Construction (Energy, shivaji University, India), (Department of Energy Technology, Shivaji University, Kolhapur)
7. N. Lloyd and V. Rangan - Geopolymer Concrete Sustainable Cement less Concrete
8. Satpute Manesh B., Wakchaure Madhukar R., Patankar Subhash V. - Effect of Duration and Temperature of Curing on Compressive Strength of Geopolymer Concrete
9. Djwantoro Hardjito, Steenie E. Wallah, Dody M.J. Sumajouw, and B.V. Rangan - Factors influencing the compressive strength of fly ash-based Geopolymer concrete
10. S. vaidya ,E. i. diaz, E. n. allouche - Experimental evaluation of self-cure geopolymer concrete for mass pour applications
11. ashida A Jhumarwala, P. S. Rao , T. N. Patel - Experimental Investigation on Self-Compacting Geopolymer Concrete (SCGC)
12. Djwantoro Hardjito, Steenie E. Wallah, Dody M.J. Sumajouw, and B.V. Rangan - Factors influencing the compressive strength of fly ash based geopolymer concrete
13. M. Olivia*, Curtin University of Technology, Australia, P. Sarker, Curtin University of Technology, Australia, H. Nikraz, Curtin University of Technology, Australia - Water Penetrability of Low Calcium Fly Ash
14. Abhijitsinh Parmar, IJPRET, 2014; Volume 3 (4): 100-106