



INTERNATIONAL JOURNAL OF PURE AND APPLIED RESEARCH IN ENGINEERING AND TECHNOLOGY

A PATH FOR HORIZING YOUR INNOVATIVE WORK



SPECIAL ISSUE FOR NATIONAL LEVEL CONFERENCE "Recent Trends and Development in Civil Engineering"

EFFECT OF BACILLUS TYPE OF BACTERIA MIXED WITH FLY ASH ON STRENGTHENING OF CRACKED CONCRETE

ABHIJITSINH PARMAR¹

1. Assistant Professor, Department of Civil Engineering, SVBIT, Gandhinagar – 382650

Accepted Date: 27/01/2018; Published Date: 01/03/2018

Abstract: Cracks are the common type of failure in concrete which are irreversible in process [1, 2] Bacillus Pasteruii, Bacillus Cohni, Bacillus Sphearicus are common soil bacterium induce the precipitation of calcite exhibited its positive potential in selectively consolidating simulated fractures in the consolidation of sand.[1, 3, 4, 5] In this study cracks of concrete were filled with different types of Bacillus bacteria mixed with Fly Ash to repair cracks. A compression, flexural and durability tested on mortar cubes and concrete beams treated with bacteria were studied. The effect of different depth of crack on the compression, flexural and durability of concrete was studied. It was found that all the increase in depth of crack reduce the strength of cubes and beams.

Keywords: Bacterial Concrete, Self-Healing, Cracks, Concrete, Repair

Corresponding Author: ABHIJITSINH PARMAR



PAPER-QR CODE

Access Online On:



www.ijpret.com

How to Cite This Article:


Abhijitsinh Parmar, IJPRET, 2018; Volume 6 (7): 370-375

INTRODUCTION


In concrete, cracking is a regular observable fact due to the comparatively low tensile strength. Many factors are affecting the durability and strength of concrete. High tensile stresses can result from external loads which lead to failure of concrete. Many methods and material are available in market to repair concrete cracks. But most of materials are not eco-friendly and cause environment pollution and due to these many are banned in many countries. Bacterial induced calcium precipitation type repairing technique is eco-friendly and has been proposed as an alternative and environmental friendly crack repair technique. *B. pasteurii* produces urease, which catalyzes urea to produce CO₂ and ammonia, resulting in an increase of pH in the surroundings where ions Ca²⁺ and CO₃²⁻ precipitate as CaCO₃. Possible biochemical reactions in medium to precipitate CaCO₃ at the cell surface that provides a nucleation site. The microbial urease catalyzes the hydrolysis of urea into ammonium and carbonate.[9] One mole of urea is hydrolyzed intracellularly to 1 mol of ammonia and 1 mole of Carbamic acid (1), which spontaneously hydrolyzes to form an additional 1 mole of ammonia and carbonic acid (2).[3, 4, 5, 6, 7, 8, 9, 10]




Ammonium and carbonic acid form bicarbonate and 2 moles of ammonium and hydroxide ions in water (3 &4).



The production of hydroxide ions results in the increase of pH, which in turn can shift the bicarbonate equilibrium, resulting in the formation of carbonate ions (5)



The produced carbonate ions precipitate in the presence of calcium ions as calcium carbonate crystals (6).



The formation of a monolayer of calcite further increases the affinity of the bacteria to the soil surface, resulting in the production of multiple layers of calcite.

Bacteria such as *Bacillus pasteurii*, *Bacillus pseudofirmus*, *Bacillus cohnii*, *Sporosarcina pasteurii*, and *Arthrobacter crystallopoietes* increase the compression strength of concrete through their

biomass. Not all bacteria increase the strength of concrete significantly with their biomass[11]. Bacillus sp. CT-5. can reduce corrosion of reinforcement in reinforced concrete by up to four times. Sporosarcina pasteurii reduces water and chloride permeability. B. pasteurii increases resistance to acid [11].146 Bacillus pasteurii and B. sphaericus can induce calcium carbonate precipitation in the surface of cracks, adding compression strength.[11]

MATERIALS AND EXPERIMENTAL PROGRAM

For casting of Mortar and Concrete beams for test OPC cement grade 53, Potable water, Fly Ash, Coarse aggregates and Bacillus type of Bacteria (Bacillus Pastuerii, Bacillus Cohni and Bacillus Sphearicus) were used. Following test was conducted with procedure to measure the effect of Bacteria on strengthening of concrete cracks repairing.



Fig. 1(a) Insertion of Bacterial paste into crack (b) Feeding Bacteria with Urathine-P

A. Compression Test

Mortar cubes were made by using ordinary Portland cement 53 Grade. Cement and Fly Ash ratio is used as 1:3 (by weight). Moulds with dimensions of 70.6 mm× 70.6 mm× 70.6 mm. After casting, all moulds were placed in a normal temperature of room with a relative humidity of more than 90% for a period of 24h. After de-moulding, the specimens were placed for the curing for 28 days. After that for 28 days different bacteria inserted in crack mixed with standard sand and after that bacteria's were feed at every 6 hours interval. And After it Compression test carried out at 7th, 28th and 56th day.

B. Flexural strength study

Concrete Beams grade M20 were made by using ordinary Portland cement. Moulds with dimensions of 500 mm× 100 mm× 100 mm. After casting, all moulds were placed in a normal temperature of room with a relative humidity of more than 90% for a period of 24h. After de-moulding, the specimens were placed for the curing for 28 days. After that for 28 days different

bacteria inserted in crack mixed with standard sand and after that bacteria's were feed at every 6 hours interval. And After it Flexural test carried out at 28th and 56th day.



Figure -3 Flexural Test setup

TEST RESULT AND DISCUSSION

The effects of the following parameters on the compression, flexural and durability of concrete were investigated:

- Depth of crack
- Number of days from healing of crack

Result of Compression, Flexural and Durability test are shown in table – 1, 2 & 3 respectively.

Table – 1 Average Compressive strength after 28 days of filling bacteria

Crack Depth	Normal Cube(Without Crack & Bacteria) (N/mm ²)	Cracked Cube (N/mm ²)	Cracked cube repair with Bacillus Pastuerii (N/mm ²)	Cracked cube repair with Bacillus Sphearicus (N/mm ²)	Cracked cube repair with Bacillus Cohni (N/mm ²)
5 mm	27.33	25.48	26.06	25.59	26.21
10 m		23.68	25.34	25.30	25.32
15 m		22.86	24.92	24.81	24.90
20 m		21.09	23.41	23.20	21.45
25 mm		19.69	22.25	21.46	21.42

Table – 2 Average Flexural Strength after 28 days of filling Bacteria

Crack Depth	Normal Cube(Without Crack & Bacteria)	Cracked Cube (N/mm ²)	Cracked cube repair with	Cracked cube repair with	Cracked cube repair with

	(N/mm ²)		Bacillus Pastuerii (N/mm ²)	Bacillus Sphearicus (N/mm ²)	Bacillus Cohni (N/mm ²)
5 mm	6.79	6.28	6.51	6.48	6.46
10 m		6.13	6.41	6.36	6.30
15 m		5.94	6.34	6.29	6.26
20 m		5.77	6.26	6.21	6.17
25 m		5.58	6.33	6.11	6.10

All the test results were compared with that of the uncracked and cracked concrete and mortar. It was found that all the specimens effectively healed which had less depth of crack.

CONCLUSIONS

- From the test results of Compression test and Flexural test, we can conclude that repaired cracked concrete with Bacillus type bacteria can be re-strengthen up to almost its original strength in case of smaller depth cracks. But in case of larger depth than 15 mm improvement in compressive strength reduces as the depth of crack increases. Because for calcite precipitation process Bacillus type bacteria needs more oxygen. Due to larger depth Bacteria didn't get enough amount of Oxygen from atmosphere.
- The use of this biological repair technique is highly desirable because the mineral precipitation induced as a result of microbial activities is pollution free and natural.
- Regain in compressive strength filled with bacteria and Fly Ash is comparatively less than results with cracked fill with bacteria and Ennore sand

REFERENCES

1. Abhijitsinh Parmar, Ankit Patel, Priyank Shah, "IMPROVEMENT OF THE CONCRETE CRACKS BY USING BACILLUS SPHAERICUS", International Journal of Engineering Development and Research (IJEDR), ISSN:2321-9939, Volume.1, Issue 2, pp.82 - 84, Sept 2014
2. Abhijitsinh Parmar, Ankit Patel, Vismay Shah , Sandeep Khorasiya, Dipan Patel. (2013). "Improvement on the concrete cracks by using Bacillus pastuerii." International Journal for Scientific Research & Development (IJSRD) | Vol. 1, Issue 1, 2013
3. H.M.Jonkers, "Bacteria-Based Self Healing Concrete",vol .56, 2011, pp.1-12.
4. Henk Jonkers, "Development And Application Of Bacteria-Based Self-Healing Materials",2012
5. Srinivasa Reddy. V, Achyutha Satya.K, Seshagiri Rao .M. V, Azmatunnisa. M, "A Biological Approach To Enhance Strength And Durability In Concrete Structures", vol. 4, 2012 , pp. 392-399.
6. Ramakrishnan, V., Bang, S.S., Ramesh, K.P., and Mulukutla, S., "Performance of Bacterial Cement", Proceedings of 24th International Conference of Cement Microscopy, San Diego, California, April 2002, pp. 336-354.

7. Ramakrishnan, V., Bang, S.S., Srinivasan Neelamegam., and Ramesh, K.P., "Durability of Cement Mortar Made With Different Concentrations of Bacteria", Proceedings of 25th International Conference of Cement Microscopy, Richmond, Virginia, April 2003.
8. Ramachandran, S.K., Ramakrishnan, V., and Bang, S.S., "Remediation of Concrete using Microorganisms", ACI Materials Journal, v.98, Jan-Feb 2001, No.1, pp. 3-9.
9. DeJong, J.T.; Fritzes, M.B.; Nüsslein, K. (2006). "Microbial Induced Cementation to Control Sand Response to Undrained Shear". Journal of Geotechnical and Geoenvironmental Engineering. 132 (11): 1381–1392
10. DeJong, J.T.; Morenson, B.M.; Martinez, B.C.; Nelson, D.C. (2010). "Bio-mediated soil improvement". Ecol. Eng. 36 (2): 197–210.
11. Navdeep Kaur Dhami; Sudhakara M. Reddy; Abhijit Mukherjee (2012). "Biofilm and Microbial Applications in Bio mineralized Concrete". Archived from the original on 19 December 2013.